

304V

Melt Practice

This austenitic stainless steel is initially electric-arc melted. Then as a refinement to the purity and homogeneity of the metal, 304V is Vacuum Arc Remelted (VAR). This process yields a more uniform chemistry with minimal voids and contaminants.

Typical Chemistry

	FWM Avg. Wt. %	ASTM A313-95
Chromium	18.58	18.0-20.0
Nickel	8.65	8.00-10.50
Carbon	0.073	.08
Manganese	1.310	2.00
Molybdenum	.16	-
Silicon	0.70	1.00
Phosphorus	0.021	.045
Copper	.17	-
Cobalt	.10	-
Nitrogen	.034	.10
Iron	Balance	Balance

FWM chemistry is for reference only, and is not to be used for specification purposes.

Physical Properties

Density	0.286 lbs/in ³
Modulus Of Elasticity	28.5 psi x 10 ⁶
Electrical Resistivity	720 μohms-mm
Thermal Conductivity	16.36 W/m K (100°C)

Thermal Treatment

In wire form, 304V will gain tensile strength when stress relieved at 350-427°C. A reducing atmosphere is preferred but inert gas can be used. 304V will fully anneal at 1010-1121°C in just a few minutes. There is a carbide precipitation phenomenon that occurs between 427 and 899°C that reduces the corrosion resistance of the alloy. American Society for Testing Materials has described a test method to ensure the alloy has not been damaged.

Applications

This alloy is the most popular for medical appliances. The ease of joining with solder or welding, combined with excellent strength makes it desirable. This alloy is also one of the least expensive medical materials. Some examples of end products are stylets, catheters, guide wires, springs and needles. Fort Wayne Metals routinely makes cables, strands, flat wire and shapes from this alloy.

Mechanical Properties

% CW	Y.S. (psi)	U.T.S. (psi)	% E (10" gauge length)
0%	50,000	107,000	41%
20%	70,000	140,000	14%
37%	90,000	184,000	4%
50%	140,000	208,000	3%
60%	160,000	229,000	2.6%
68%	180,000	247,000	2.7%
75%	200,000	265,000	2.6%
80%	215,000	272,000	2.9%
84%	230,000	289,000	2.5%
90%	245,000	306,000	2.6%
93%	250,000	316,000	2.7%
95%	280,000	334,000	2.6%

Values are typical and may not represent all diameters. Test method will affect results.

Surface Conditions

Stainless steels develop a highly polished appearance as they are drawn to fine diameters. Surface roughness can be less than 5 RMS when processed using SCND* dies and measured with a profilometer. Diameters over .040" are finished with polycrystalline dies and exhibit a rougher surface than natural diamond dies. Diameters over .100" have an even rougher surface because they are drawn with carbide dies.

*SCND means single crystal natural diamond.

Customer Commitment

As a leading manufacturer of medical grade wire, we fully support our customers' requirements for quality, service, reliability, dependability and research and development projects. We are FDA and ISO 9002 registered. We are fully capable of statistical process controls and just-in-time inventory scheduling.

At Fort Wayne Metals, we're committed to working with each of our customers to ensure that we meet their specific needs.

Standard Products and Services

Available Alloys

(Not all types stocked)

Nitinol
Titanium
304V
304LV
316LVM
DFT (Composites)
MP35N®
L-605
CONICHROME®
CCM®
HASTELLOY® Alloy C-276
HAYNES® 214™
17-7PH®
CUSTOM® 455
BIODUR® 108
WASPALLOY®

Processing Capabilities

Diamond Drawing
Strand Annealing
Custom Spooling
Flat Drawing
Flat Rolling
Custom Stranding and Cabling
Straightening and Cutting
Lab Services

Product Uses

BioConductors
Catheter Guides
Orthopaedics
Orthodontics
Surgical Needles
Surgical Staples
Suture Wire
Stents
And Other Demanding
Medical Products

17-7PH is a registered trademark of Armoc, Inc.

CUSTOM 455, BIODUR, CCM and CONICHROME are registered trademarks of Carpenter Technologies, Inc.

HAYNES, HASTELLOY and 214 are registered trademarks of Haynes International, Inc.

MP35N is a registered trademark of SPS Technologies.

WASPALLOY is a registered trademark of United Technologies Corporation.



U.S. office:
9609 Indianapolis Road
P.O. BOX 9040
Fort Wayne, IN 46899

Tel. (260) 747.4154
Fax (260) 747.0398

European office:
Aalsterweg 110D
5615 CJ Eindhoven

Tel. +(31) 40212 7828
Fax +(31) 40212 7864
www.fwmetals.com

Properties Data:

The data and information provided are based on work conducted principally by Fort Wayne Metals Research Products Corp. and occasionally supplemented by information from the open literature, and are believed to be reliable. However, we do not make any warranty or assume any legal liability or responsibility for its accuracy, completeness or usefulness, nor do we represent that its use would not infringe upon private rights. Any suggestions as to uses and applications for specific alloys are opinions only and Fort Wayne Metals Research Products Corp. makes no warranty of results to be obtained in any particular situation. For specific concentrations of elements present in a particular product and a discussion of the potential health effects thereof, refer to the Material Safety Data Sheet supplied by Fort Wayne Metals Research Products Corp.